

## QuickCoat – Base Protect (RAL/WE) – 2 component coating – aliphatic

POLYUREA

### 1. Characteristics:

**QuickCoat – Base Protect (RAL/WE)** is a premium, 2-component high solid coating, based on polyaspartic-technology, derived from a reaction of an aliphatic isocyanate Pre-Polymer and an amine terminated resin blend. On account of the UV- and colour fast properties it will be used amongst others as thin layer coating for surface protection and/or sealing (interior and outdoor area) on existing coating systems, but it is also designed for the classic corrosion protection of industrial constructions. **QuickCoat – Base Protect (RAL/WE)** can be installed on miscellenous substrates or surfaces and therefore it creates a flexible, durable, tough surface. **QuickCoat – Base Protect (RAL/WE)** can be applied with brush, roller or airless-sprayed as stand-alone system or as top coat for existing coting systems

### 2. Features:

- **Excellent color retention, UV resistant**
- **Very good adhesion on concrete structures without using a primer**
- **Superior chemcial resistance compared to a multitude of solvent agents**
- Fast reactivity and cure times
- Fast return to service time > long life-cycle > almost maintenance free > significant savings
- Excellent Top Coat on existing aromatic Polyurea Coatings
- Maintains flexibility > seamless and joint-less coating and lining
- Resistant to most chemicals, solvents, acids and caustics
- Good outdoor weathering > resistant to chlorine- and saltwater
- Hydrolysis firm > non sensitive to humidity
- Thermal stable
- Very good bonding properties to concrete and steel substrates
- Moderate impact & abrasion resistance
- Nearly no odor and VOC-free
- With no catalysts
- Broad colour spectrum ( RAL)

### 3. Typical Uses:

- As UV- and colour-fast Top Coat or sealing on existing base coats for flooring and roofs etc.
- For high quality optically demanding and decorative coatings of pools, furniture or model making.
- Optimization of the weathering and anti aging properties of GRP-formed parts (e.g. window frame)
- Interior and exterior coating of tanks as long-term corrosion protection in the petrochemical industry
- As inner- and outer pipeline coating for the oil- and gas industry
- Atmospheric corrosion protection of industrial and civil constructions (e.g. helideck, Off-shore-plants)

**QuickCoat – Base Protect (RAL/WE) – 2 component coating – aliphatic**
**POLYUREA**

<b>4. Processing properties:</b>	<b>Datas</b>	
Mixing ratio of Comp. A to Comp. B	55 : 100 per weight for <b>Base Protect</b> 65 : 100 per weight for <b>Base Protect RAL/WE</b>	
Material consumption [g/m <sup>2</sup> ]	ca. 250 – 500; dependent of the kind of application (Roller, Spray)	
Recommended thickness [µm]	ca. 100 – 250 (for each layer)	
Numbers of layer	1 – 2 (also multi layer possible)	
Gelification time at 20 °C [min.]	40 - 60	15 - 25 (with accelerator-solution)
Waiting time between the single layers* [h]	1	0,5 (with accelerator-solution)
Dust dry time* [h]	1 - 2	0,5 - 1 (with accelerator-solution)
Walkable after* [h]	2 - 3	1 - 2 (with accelerator-solution)
Curing* (Normal loading) [h]	16 - 24	8 – 12 (with accelerator-solution)
Temperature range for application (ambience) [°C]	+5 - +50	
Temperature range for application (substrate) [°C]	+5 - +50	
Material temperature (QSP Top Coat) [°C]	20 (preferred)	
Maximal relative air humidity for application [%]	98	
Pay attention to the dew point limit	min. 3K > DP (dew point)	

<b>5. Physical Properties:</b>	<b>Datas</b>		
Chemical Base	-	Comp. A: HDI-Prepolymer Comp. B: Mod. Polyaspartics	
VOC-content [%]	DIN EN ISO 11890-1 / ASTM D-1259	10; VOC-free according to 1999/13/EC	
Solids content [%]	DIN EN 827 / ASTM D-2697	90	
Colour	-	Different (on request)	
Viscosity [mPa*s] @ 25 °C	DIN EN ISO 2884-2 ASTM D-4878	Comp. A: 50 - 150	Comp.B: ca.. 5.000 Mix: ca. 1.900
Density [g/cm <sup>3</sup> ] @ 20 °C	DIN EN ISO 2811-1 / ASTM D-1217	Comp. A: 1,10 – 1,14	Comp. B: 1,33 – 1,37 1,31 – 1,35 Mix: ca. 1,26 ca. 1,24
Density [g/cm <sup>3</sup> ]	EN ISO 1183 / ASTM D-792	1,15 ± 0,02	
Tensile strength [MPa]	ISO 37-2005 / ASTM D-638	≥ 19	
Elongation at tear [%]	ISO 37-2005 / ASTM D-638	≥ 25	
Hardness [Shore D]	ISO 868-2003 / ASTM D-2240	65 ± 5	
Taber Abrasion [mg]	ASTM D-4060	< 25 ( Wheel CS17 / 1.000g / 1000 cycles)	
Climate-Test [ΔE* <sub>ab</sub> ]	ISO 4892-2 Teil A	After approx. 2,5 Years: < 1,5 (not observably with the naked eye)	
Pull off strength [N/mm <sup>2</sup> ]	DIN EN ISO 4624 / ASTM D-4541	Polyurea: ≥ 4	Steel: ≥ 4 Concrete: ≥ 1,5
Max. Process temp. [°C]	ISO 11346 / ASTM D-2485	Wet: 60	Dry: 120 Peak temperature dry: 140
Storage conditions [°C]	DIN EN 12701 / ASTM	10 – 30 (in closed original drums, stored at dry and well ventilated place; beware of freezing)	
Shelf life	-	12 months	

\*) All measurements at 23 °C @ 50%rF. Deviations at different ambient conditions have to be taken into account.

## QuickCoat – Base Protect (RAL/WE) – 2 component coating – aliphatic

POLYUREA

### 6. Hints for application:

Before using both components have to be stirred well and then component A has to be filled into component B completely and mixed carefully with an adequate agitator.

After mixing both components you should allow the mixture to rest for a few minutes (2-3 min).

**QuickCoat – Base Protect (RAL/WE)** should be applied preferably by roller (solvent resistant roller, mohair roller or similar) or alternatively by spraying in a conventional way with air pressure or airless application.

#### QuickPlus Agent DLU (Diluter):

The aforementioned additive **QuickPlus Agent DLU** is suitable for the adjustment of the viscosity for the corresponding application:

**Brush, Roller:** 0 – 5% per weight relating to the mixture A+B

**Spray, conventionell with compressed air or Airless:** 0 – 15% per weight relating to the mixture A+B

#### QuickPlus Agent ACC (Accelerator-Solution):

For adjusting the gelification time respectively the curing time considering certain circumstances (like e.g. the ambient temperature or a short shut-down-window) it is possible under the support of the **QuickPlus Agent ACC** (accelerator-solution) to reduce the aforementioned application times.

Hereby has to be filled the content of **QuickPlus Agent ACC** completely in component B (equates approx. 1.5% per weight of component B), after component B was stirred well before.

The drying times depend naturally on the climate and environmental influences, e.g. ambient temperature, relative humidity of air and ventilation etc.

Therefore the times specified can only be used as guidelines. The exact times have to be determined by testing on site.

#### Cleaning of the spray equipment (conventionell or airless-machines):

After the application of **QuickCoat – Base Protect (RAL/WE)** with the spray machine is finished, all parts of the spray equipment, which come in contact with the material, have to be cleaned and flushed carefully with organic solvent like e.g. acetone, MEK, MIBK, Xylene or similar solvents.

#### **IMPORTANT:**

Using as a Top Coat respectively as a sealing of body layers based on aromatic polyurea coating systems e.g. QSP Industrial, the base coat must be primed first with **QPR 1K-PU universal** and then applying the **QuickCoat – Base Protect (RAL/WE)**.

As soon the primer displays a tack-free surface, earliest after approx 1 – 2 hours, dependent of the conditions of the surrounding, but latest after 6 – 12 hours the primer must be overcoated with **QuickCoat – Base Protect (RAL/WE)**.

Furthermore it have to be taken into account that at the beginning of the design the sealing with **QuickCoat – Base Protect (RAL/WE)** of aromatic Polyurea body layers will be done in the same colour shade (similar RAL-tone) or at least the base coat should display a RAL-tone 7035 (light grey) or more bright, because the covering power of **QuickCoat – Base Protect (RAL/WE)** is not sufficient enough to compensate significant differences in the contrast (like e.g. covering dark grey with white colour).

On account of this fact it would be indicated to apply a small test area in each case before starting with the project in order to double check the covering power.

**QuickCoat – Base Protect (RAL/WE) – 2 component coating – aliphatic**

**7. Form of delivery:**

<b>Product name</b>	<b>Unit</b>	<b>Ref.-No.</b>
<b>QuickCoat – Base Protect Comp. A+B</b>	<b>5,5 kg / 10 kg</b>	<b>On Request</b>
<b>QuickCoat – Base Protect Comp. A+B</b>	<b>2,75 kg / 5 kg</b>	<b>On Request</b>
<b>QuickCoat – Base Protect Comp. A+B</b>	<b>0,55 kg / 1 kg</b>	<b>On Request</b>
<b>QuickCoat – Base Protect RAL/WE Comp. A+B</b>	<b>6,5 kg / 10 kg</b>	<b>On Request</b>
<b>QuickCoat – Base Protect RAL/WE Comp. A+B</b>	<b>3,25 kg / 5 kg</b>	<b>On Request</b>
<b>QuickCoat – Base Protect RAL/WE Comp. A+B</b>	<b>0,65 kg / 1 kg</b>	<b>On Request</b>
<b>QuickPlus Agent DLU</b>	<b>5 l</b>	<b>On Request</b>
<b>QuickPlus Agent DLU</b>	<b>1 l</b>	<b>On Request</b>
<b>QuickPlus Agent ACC</b>	<b>150 g</b>	<b>On Request</b>
<b>QuickPlus Agent ACC</b>	<b>75 g</b>	<b>On Request</b>
<b>QuickPlus Agent ACC</b>	<b>15 g</b>	<b>On Request</b>

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein is the only one which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and VIP GmbH makes no claim that these tests or any other tests, accurately represent all environments.

The laws of the purchaser regarding of the quality of our materials follows completely our general terms and conditions. For requirements, which exceed the scope of the above mentioned applications, contact our technical staff at any time under the following number +49-(0)89-89 55809 30.

Valid is only the actual version of this technical data sheet in each case.

© Copyright, VIP GmbH, QuickCoat – Base Protect (RAL/WE)

**Version: July 2012-001**